



الواحة للدهانات

ALWAHA PAINTS

منذ 1989 Since



دهانات العوازل و الحماية
Isolators & Protection Paints

قطرمينة

مستحلب إسفلتي مائي عازل، شديد التحمل

QATERMENA

Bitumen Emulsion, Heavy duty Insulator

الوصف

مستحلب إسفلتي بأساس مائي بلون بني غامق يتحول بعد الجفاف إلى طبقة حماية مرنة، عازلة، سوداء اللون، شديدة التحمل ضد الماء و الرطوبة.

المميزات

- ذو مرونة عالية و مقاوم للصدمات.
- سائل عالي القوام متجانس، يستعمل على البارد.
- يكون بعد جفافه طبقة عازلة غير منفذة للماء، عالية المرونة .
- ثابتة الكفاءة في درجات الحرارة (-10 : 100) درجة مئوية.
- مقاوم جيد لجميع أنواع الكيماويات التي عادةً ما تتعرض لها المنشآت.
- له قوة تماسك و إلتصاق كبيرة على الأسطح الجافة و الرطبة.
- لا يشتعل لأنه ذو اساس مائي.
- يصلح لعزل الأنابيب و المواسير و الخزانات المدفونة بالأرض.
- يصلح بصفة عامة لأعمال العزل ضد المياه للخرسانة و الأسطح الإسمنتية و الأسقف المختلفة.

تعليمات الإستخدام

1. يراعى نظافة السطح المراد دهانه وخلوه من الأوساخ و أي مواد عازلة مثل (الشحوم و الزيوت) لضمان قوة الإلتصاق.
2. يتم دهان طبقة برايمر من قطرمينة الواحة مخفف بنسبة 2:1 لضمان الإلتصاق الجيد مع السطح.
3. يدهن طبقتين إلى ثلاث طبقات باستعمال الفرشاة (لا يزيد التخفيف عن 10%) مع ترك فترات زمنية للجفاف من 8-12 ساعة.

أدوات التطبيق

الفرشاة - الرولة

معدل الفرد

1.5 - 3 كجم / متر مربع (للوحة الواحد معطياً سمك 750 ميكرون بعد الجفاف).

Description

Is a bitumen emulsion water based for insulation works, it is brown color dries to very elastic proofing layer black highly resistant to water and moisture membrane.

Features

- Is thick homogeneous liquid cold applied.
- It is very elastic and no cracking or flaking.
- Dries to form a rubber elastic membrane impervious to damp and water and resistant to cold and heat from (-10 / 100oC)
- Is highly resistant to all chemical action normally occurring in building structures..
- Excellent adhesion into wet and dry surfaces.
- As a vapour barrier for both above and below applications.
- As general purpose damp proof coating for concrete.

Instructions for use

1. Surface must be clean, free from oil, grease, dirt, ..., etc.
2. The first coat to be applied as priming coat (diluted 1:2) with fresh clear water.
3. Allow 8:12 hours to dry then apply 2-3 coat (diluted 10%)

Application tools

Brush-Roller

Spreading Rate

1.5-3kg/m2 (According to surface nature)