



الواحة للدهانات ALWAHA PAINTS

منذ 1989 Since



الدهانات المائية
Waterbase Paints

الواحة لاتكس

دهان مائي اقتصادي مطفى للأسطح الخارجية والداخلية

ALWAHA LATEX

Water Based Paints for Exterior & interior surface

الوصف
دهان بلاستيك فائق الجودة مصنع من أجود أنواع الراتنجات المستحلبة قابل للغسيل ومناسب لتغطية كافة الأسطح الأسمنتية (خارجيا/داخليا)

المميزات
• ناصع البياض. • ذو تغطية ومعدل امتداد عاليين. • يستخدم خارجيا و داخليا. • ذو قوة التصاق كبيرة. • يعطى سطحا جذابا ناصع البياض وبدون لمعان. • صديق للبيئة وخالي من الرصاص .
تعليمات الاستخدام

(1) إعداد السطح:-

- يراعى نظافة السطح المراد دهانه وخلوه من الزيوت والأتربة.
- فى حالة تطبيق المنتج على أسطح مدهونة مسبقا يراعى نظافة السطح وإزالة طبقة الدهانات الغير متماسكة وخلو السطح من أى مواد غريبة لضمان قوة الالتصاق.
- يراعى معالجة الأسطح المسامية باستخدام السيلر قبل تطبيق المعجون.

(2) خطوات التطبيق :-

- يستخدم برايمر الواحة أو سيلر الواحة لغلق المسام قبل تطبيق المعجون.
- يتم تطبيق معجون الواحة دون إضافات.
- يراعى صنفرة سطح المعجون قبل تطبيق الدهان المناسب.
- ينصح بعمل طبقة من برايمر الواحة أو سيلر الواحة فوق المعجون وقبل الدهان لزيادة معدل فرد الدهان.
- يخلط الدهان جيدا ويخفف بالماء حتى القوام المناسب (وإذا يزيد التخفيف عن 10%)

أدوات التطبيق
الفرشاة – الرولة

معدل الفرد
7-9 م ² / لتر (ويتوقف ذلك على طبيعة السطح وسمك الطبقة الجافة المقترحة من 30-40 ميكرون) .

Description
Alwaha Latex high quality plastic paint ,suitable for Exterior & interior surface

Features
• Bright White • High spreading rate. • High strong adhesion. • Gives a beautiful bright surface without glossiness. • Environment friendly, lead free.

Instructions for use

1)Surface preparation:-

- Surface must be clean, free from oil, grease, dirt... etc.
- Old painted surfaces should be cleaned first from all loose paint and other materials that can affect adhesion.
- Absorbent substrates should be moistened with alwaha sealer before putty.

2)Application steps:-

- Use sealer & primer alwaha for priming purposes. - Alwaha putty to be applied without further additions.
- Substrate should be sanded and then apply the Galaxy paint.
- The use of a sealer-primer alwaha after puttying and before painting is recommended in order to increase spreading rate of finish paint.
- Mix alwaha Latex thoroughly before application, thinned with clean water up to a maximum of 10% .

Application tools
Brush-Roller

Spreading Rate
7-9m ² /kg (according to surface nature, recommended DFT from 30 to 40µm/coat).

